

# RUBBERFLEX FLEXIBLE DUCT CONNECTOR

## TECHNICAL DATA SHEET

| Property                    | Value / Assessment   | Test Method  |
|-----------------------------|----------------------|--|
| Basic Fabric Coating        | Polyester Yarn Vinyl | Woven Fibreglass Neoprene Silicone Rubber Hypalon Polyurethane |
| Weight                      | 576 gms / sq.mtr     |  |
| Tear Strength               | 45 X 45 kgs          | ASTM D 751   |
| Tensile Strength            | 108 X 100 kgs        | ASTM D 751   |
| Operating Temperature Range | -40 °C to +93°C      | up to 300°C for Silicone Rubber                                |
| Burst Strength              | 400 psi              | Up to 800 psi for Hypalon                                      |
| Fire Rating                 | Class A              | ASTM E-84  |