

# RUBBERFLEX FOSTER 30-36

## TECHNICAL DATA SHEET

Property	Value / Assessment	Test Method
Solid content	60%	
Drying time	2 hours	
Adhesion strength	2.25 N/mm <sup>2</sup>	
Operating Temperature Range	-15 °C to +85 °C	
Fire properties	<25/50	ASTM E 84