

RUBBERFLEX XLPE

TECHNICAL DATA SHEET

Property	Value / Assessment	Test Method
Material	Crossed link Polyolefin Foam	
Density	25 -35 Kg/m3	ASTM D 1622
Thermal Conductivity (k) at 35 deg C mean temperature	0.0321 W/m-K	ASTM C518 -17
Operating Temperature Range consult salesperson for applications with temperatures below (-)40°C & higher than (+)105 °C	-80 °C to +105 °C	ASTM C 534
Anti-Fungal	NO GROWTH	
Fire Rating	Class 1	BS 476 Part 7