

RUBBERFLEX NBR FOAM TAPES

TECHNICAL DATA SHEET

Property	Value / Assessment	Test Method
Backing thickness	3±1 mm	
Tensile Strength	>210n/in	
Elongation at Break	>155	ASTM D 3759
Thermal conductivity	0.032 W/mK	ASTM C 518
Operating Temperature Range	-40 °C to +93°C	up to 300°C for Silicone Rubber
Water permeability	0 perm.in	ASTM-E96
Fire Rating	Class A	ASTM E- 84