RANGE OF PRODUCTS

RUBBER FLEX ULTRA

TECHNICAL DATA SHEET

Property	Value/Assessment	Test method
Material	Closed Cell NBR elastomeric Foam	
Thermal conductivity (k) at 35 deg C mean temperature	0.0321 W/m - K	ASTM C518 -17
Water vapour transmission	0.00 Perm in	ASTM E96 / 96M
Operating temperature range consult salesperson for applications with temperatures below (-)40°c & higher than (+)105 °c	-183 °C to +105 °C	ASTM C 534
Cfc, hcfc. VOC & rohs SUSTANABILITY	NON-DETECTED OZONE DEPLETION POTENTIAL = 0	CERTIFIED GREEN BUILDING PRODUCT
Bacterial & fungal resistance	EXCELLENT	ASTM G21 ISO 22196